

Quartz Countertops



UNIVERSAL





3008 Star Cluster

3015 Sunburst

STANDARD SIZES

ITPE						
Kitchen	108-in x 26-in	96-in x 26-in	78-in x 26-in	70-in x 26-in	48-in x 26-in	
Penninsula	108-in x 26-in	96-in x 26-in	78-in x 26-in	70-in x 26-in	48-in x 26-in	
Island	108-in x 44-in	108-in x 42-in	96-in x 40-in	96-in x 36-in	72-in x 36-in	
Vanity	73-in x 22-in	61-in x 22-in	49-in x 22-in	37-in x 22-in	25-in x 22-in	
Large Slab	118-in	x 55-in (Standa	rd) 126	-in x 63-in (Jum	nbo)	

THICKNESS OPTIONS

Available in both 2-cm and 3-cm thickness options.

The lead time is 90 days from order placement.

EDGING OPTIONS

Full Bullnose, Demi Bullnose, Eased, 1/4 Top & Bottom Round, Top Bevel, & Double Bevel.

INSTALLATION

Install in accordance with Wagonway Installtion Instructions.

WARRANTY

LEAD TIME

BENEFITS PROPERTY Non Porous Scratch Resistant Stain Resistant

Heat Resistant Low Maintenance Resistance to Chemicals

Wagonway product warranty includes up to 7-year light commercial. Please visit www.wagonway.com for full warranty details.

Yes

BETTER 10 YEAR RESIDENTIAL 7 YEAR LIGHT COMMERCIAL

No





3018 Full Moon



	QUARTZ	GRANITE	MARBLE	
	Yes	No	No	
t	Yes	Yes	No	
	Yes	No	No	
	Yes	Yes	Yes	
;	Yes	No	No	

No

3019 Dark Matter



Quartz Countertops



The collection is an assortment of colors and patterns to accentuate boldness within our universe. This collection is the eye-catching element that creates a focal point within a space.

DESCRIPTION

Quartz stone is one of nature's hardest minerals, and through revolutionary technology we have created a modern, natural, and luxurious surface that is non-porous, stain resistant, and practically maintenance free. Quartz stones are the ideal and most practical choice for multifamily applications. We offer slabs as well as pre-fabricated and fully-fabricated countertops for easy installation.

COMPOSITION

DESCRIPTION	RATIO
Unsaturated Polyester Reson	10% - 15%
Fine Quartz Powder, Titanium Dioxide	~30%
Pigment	3%
Fine Quartz Sand	52% - 57%
Curing Agent, Coupling Agent, Cobalt Water	Trace
Brightening Agent	0.10%

TESTING

DESCRIPTION	ST
Absorption	AS
Density	AS
Mohr's Hardness	E١
Compressive Strength	AS
Stain Resistance (Polished)	A١
Chemical Resistance (Polished)	AN
Temperature Resistance	NS
Food Suitability	NS
Chemical Emissions	UL

TANDARD STM C97/C97M-15 STM C97/C97M-15 N 101:1991 STM C170/C170M-15B NSI Z124.6-2007 NSI Z124.6-2007 ISF/ANSI 51 ISF/ANSI 51 ISF/ANSI 51

Pass (0.03%) Pass (2287 kg/m3) Pass (7) Pass (Dry: 234 MPa) Pass (R=56, D=0.04-mm) Pass (Unaffected) Pass (572 deg. F) Pass Pass

RESULT




3008 Star Cluster

3015 Sunburst



3017 Milky Way



3018 Full Moon

